

# Terrazine®

A zinc-free, transparent, fast drying sealer formulated for porous masonry floors like terrazzo and Saltillo tile. Terrazine is "internally plasticized" to do a better job of filling the porosity of the floor, resulting in quick film formation in fewer coats. Terrazine is good for use on cold floors above 50 degrees.

- Zinc-free, fast drying sealer.
- Quick film formation requires fewer coats.
- Especially tolerant of cold floors.

## Technical Specifications

Appearance	Milky Emulsion
Dilution Rate	RTU
Color	White
Scent	Non-Objectionable
Non Volatile Matter	22.0%
pH @ 25 deg. C	7.50 - 8.50

## HMIS (Concentrate/RTU)

Flammability = 0      Health = 0      Reactivity = 0

## Certifications, Registrations & Notes

UL Approved

Classified by Underwriters Laboratories, Inc. as to slip resistance. (186S).



## Safety

See material safety data sheet and product for safety information, handling and proper use.

## Availability

HIL0033806	4 - 1 Gallon Containers
HIL0033807	1 - 5 Gallon Bag-In-Box
HIL0033809	1 - 55 Gallon Drum

## Directions

**Preparation: New floors:** For hard floors, allow surfaces to set 30 days to ensure proper curing of Portland terrazzo or grout joints; for resilient flooring, ensure the adhesive has cured for at least 2 weeks. Scrub with a solution of Hillyard Recoat Prep<sup>®</sup> or Assurance<sup>®</sup>, following label directions, and a blue pad. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse<sup>®</sup> and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour. **Stripping:** Strip existing polishes from the floor with a solution of Hillyard Arsenal<sup>®</sup> Stripper, Devastator<sup>®</sup>, or Power-Strip<sup>®</sup>, following label directions. Pick up scrubbing solution with an automatic scrubber or wet vacuum. Flood rinse with a solution of Hillyard Nutra-Rinse and pick up solution with an automatic scrubber or wet vacuum. Damp mop rinse twice with water and allow to dry for at least 1 hour.

**Application:** Apply 2 coats of Terrazzine at a rate of 1500-2000 ft<sup>2</sup>/gal with a microfiber flat finish mop or Multi-Flo<sup>®</sup> XP. Allow the first coat to dry a minimum of 30 minutes before applying the next. Terrazzine is to be used as a seal only and must be top-coated with a Hillyard floor polish. Once the coats of Terrazzine are dry, top-coat with a Hillyard floor polish, following label directions.

**NOTE:** Allow for longer dry time between coats of finish if the humidity is above 80% or the floor temperature is below 60 °F (16°C). For best results, do not apply more than 3-4 total coats of seal/finish per day.

**NOTICE:** Do not pour unused seal back into the original container.

(UL LOGO) FLOOR COATING AND FINISHING MATERIAL AS TO SLIP RESISTANCE ONLY. 186S